

Aluminium Alloy L93 (AMS 4029) Plate



SPECIFICATIONS

Commercial	2014A
------------	-------

Applications:

High strength structural components for aircraft , military vehicles and bridges, weapons manufacture, structural applications.

Characteristics:

Heat treatable alloy. High mechanical strength slightly higher than 2011 and 2017A.

CHEMICAL COMPOSITION

BS 2L93(1971) Alloy L93	
Element	% Present
Copper (Cu)	3.9 - 5
Manganese (Mn)	0.4 - 1.2
Silicon (Si)	0.5 - 0.9
Magnesium (Mg)	0.2 - 0.8
Iron (Fe)	0.5 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Zinc (Zn)	0.2 max
Nickel (Ni)	0.2 max
Chromium (Cr)	0.1 max
Tin (Sn)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Aluminium alloy L93 - 2014A is covered by Standard BS EN 2100 and has similarities to the following standard designations and specifications **but may not be a direct equivalent:**

2014 / 2014A AMS 4029

TEMPER TYPES

The most common tempers for L93 - 2014A aluminium are:

- T4 - Solution heat treated and naturally aged to a substantially stable condition
- T6 - Solution heat treated and artificially aged
- T651 - Solution heat treated, stress relieved by stretching then artificially aged

SUPPLIED FORMS

L93-2014A aluminium is supplied in Plate

- Plate

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2800 g/cm ³
Melting Point	640 °C
Thermal Expansion	22.8 x10 ⁻⁶ /K
Modulus of Elasticity	73000 GPa
Thermal Conductivity	134 - 135 W/m.K

MECHANICAL PROPERTIES

These Mechanical Properties apply to plate in the T651 temper

Thickness (mm)	Proof strength (Min)	Tensile Strength (Min)	Elongation % (Min)
Over 6 up to & incl. 12.5	410	460	7
Over 12.5 up to & incl. 25	410	460	6
Over 25 up to & incl. 40	400	450	5
Over 40 up to & incl. 63	390	430	5
Over 63 up to & incl. 90	390	430	4
Over 90 up to & incl. 115	370	420	4
Over 115 up to & incl. 140	350	410	4

CONTACT

Address:	Gould Alloys Ltd Markham Lane Markham Vale Chesterfield S44 5HS United Kingdom
Tel:	+44 (0) 1246 263300
Email:	sales@gouldalloys.co.uk
Web:	www.gouldalloys.co.uk

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.