

## Aluminium Alloy

### QQ-A-225/9 T7351 Bar

#### SPECIFICATIONS

|            |                  |
|------------|------------------|
| Aerospace  | QQ-A-225/9 T7351 |
| Commercial | 7075             |

A high strength aerospace aluminium alloy offering good corrosion resistance.

#### CHEMICAL COMPOSITION

| SAE AMS QQ-A-225/9<br>Alloy QQ A 225/9 |             |
|----------------------------------------|-------------|
| Element                                | % Present   |
| Zinc (Zn)                              | 5.1 - 6.1   |
| Magnesium (Mg)                         | 2.1 - 2.9   |
| Copper (Cu)                            | 1.2 - 2     |
| Iron (Fe)                              | 0.5 max     |
| Silicon (Si)                           | 0.4 max     |
| Manganese (Mn)                         | 0.3 max     |
| Chromium (Cr)                          | 0.18 - 0.28 |
| Titanium (Ti)                          | 0.2 max     |
| Others (Total)                         | 0.15 max    |
| Other (Each)                           | 0.05 max    |
| Aluminium (Al)                         | Balance     |

#### TEMPER TYPES

Alloy QQ-A-225/9 is supplied in a range of tempers:

- T651 - Solution heat treated, stress relieved by stretching then artificially aged
- T7351 - Solution heat treatment then specially artificially aged for resistance to stress corrosion.

#### SUPPLIED FORMS

Alloy QQ-A-225/9 T651 is supplied in bar/rod

- Bar

#### GENERIC PHYSICAL PROPERTIES

| Property               | Value                     |
|------------------------|---------------------------|
| Density                | 2.81 g/cm <sup>3</sup>    |
| Melting Point          | 635 °C                    |
| Thermal Expansion      | 23.5 x10 <sup>-6</sup> /K |
| Modulus of Elasticity  | 72 GPa                    |
| Thermal Conductivity   | 134-160 W/m.K             |
| Electrical Resistivity | 40 % IACS                 |

'Typical' Physical Properties are given

#### MECHANICAL PROPERTIES

| SAE AMS QQ-A-225/9<br>Bar<br>12.7mm to 76.2mm |             |
|-----------------------------------------------|-------------|
| Property                                      | Value       |
| Proof Stress                                  | 386 Min MPa |
| Tensile Strength                              | 469 Min MPa |
| Elongation A50 mm                             | 10 Min %    |

Mechanical Properties are for T7351 temper Bar in diameters 12.7mm to 76mm

## CONTACT

|          |                                                                                               |
|----------|-----------------------------------------------------------------------------------------------|
| Address: | Gould Alloys Ltd<br>Markham Lane<br>Markham Vale<br>Chesterfield<br>S44 5HS<br>United Kingdom |
| Tel:     | +44 (0) 1246 263300                                                                           |
| Email:   | <a href="mailto:sales@gouldalloys.co.uk">sales@gouldalloys.co.uk</a>                          |
| Web:     | <a href="http://www.gouldalloys.co.uk">www.gouldalloys.co.uk</a>                              |

## REVISION HISTORY

|                   |                 |
|-------------------|-----------------|
| Datasheet Updated | 14 January 2019 |
|-------------------|-----------------|

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.